

Fig.1





Fig.2

sample : K5945 file : .0633 date : 28-Aug-00 16:23 observer : rint
 comment : K.Hidaka memo :



peak data

25-1133

Al N
 Aluminum Nitride

48-0055

Ce Al11 O18
 Aluminum Cerium Oxide

46-0394

Sm Al O3
 Aluminum Samarium Oxide

Fig.3

$\text{Al}_2\text{O}_3\text{-Sm}_2\text{O}_3$






Fig.4



BEST AVAILABLE COPY

Fig.5



BEST AVAILABLE COPY

Fig.6




BEST AVAILABLE COPY

Fig.7




BEST AVAILABLE COPY

Fig.8




BEST AVAILABLE COPY

Fig.9



BEST AVAILABLE COPY

Fig.10



BEST AVAILABLE COPY

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.